

# R Silver 20 - 9 mil - Reflective Interior Films

Bold, efficient, high energy saving Safety Film



Safety

## R Silver 20 - 9 mil

**R Silver 20 - 9mil** Reflective interior window films combine the reinforced protection of security laminates with superb heat rejection, UV block, and a sophisticated appearance.

Optical and Solar Properties**	R Silver 20 - 9 mil	
Item Number	R24603T PS	
Pane	Single	Double
Visible Light Transmitted	20%	19%
Visible Light Reflected (Interior)	61%	61%
Visible Light Reflected (Exterior)	57%	56%
Ultra Violet Block	99%	99%
Total Solar Energy Reflected	50%	46%
Total Solar Energy Transmitted	15%	13%
Total Solar Energy Absorbed	35%	41%
Emissivity (Room Side)	0.91	0.91
Glare Reduction	78%	77%
Selective InfraRed Reduction (SIRR)	92%	92%
InfraRed Energy Rejection (IRER)	80%	80%
Shading Coefficient	0.30	0.40
Solar Heat Gain Coeff. (G-Value)	0.25	0.34
U-Value Winter (IP)	1.08	0.49
U-Value Winter (SI)	6.13	2.78
Luminous Efficacy	0.67	0.48
Total Solar Energy Rejected (%)	75%	66%
Mechanical Properties	R Silver 20 - 9 mil	
Thickness	9 mil	
Tensile Strength at Break	28,500 PSI	
Break Strength	245 lb/inch	
Elongation at Break	125%	
Peel Strength	7 lb/inch	

\*\* Performance results are calculated on 3 mm glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards and are only intended for estimating purposes.

S92980 3/19



Graphics  
Solutions

**Avery Dennison Graphics Solutions**

Norton Parkway 8080

Mentor, Ohio 44060

T: 1-800-660-5559

[windowfilm.orders@averydennison.com](mailto>windowfilm.orders@averydennison.com)